

Abstract

A powder core is obtained by compaction-forming magnetic powder. The magnetic powder is an alloy comprising 1-10 wt% Si, 0.1-1.0 wt% O, and balance Fe. An insulator comprising SiO_2 and MgO as main components is interposed between powder particles having a particle size of 150 μm or less.